



X - RAY TEST RECORD

F I S C H E R T E C H N O L O G Y  
EXCELLENCE WIRE INDUSTRIAL CO., LTD.  
TELEPHONE : (03)3222129

BATCH NO: DATE : 2013/02/21  
PART NO: 4DAW006-001 Q'TY : kg.  
BATCH SIZE : 6 μ" NAME : 簡秋鳳

N = 1	Au =	6.469	μ"	Ni =	69.81	μ"
N = 2	Au =	6.609	μ"	Ni =	78.96	μ"
N = 3	Au =	6.633	μ"	Ni =	73.54	μ"
N = 4	Au =	6.940	μ"	Ni =	69.99	μ"

F I N A L RESULT

THICKNESS MEASUREMENT

APPLICATION NO. = 5 0606

M E A N THICKNESS	=	6.66	=	73.1
STANDARD DEVIATION	=	0.20	=	4.28
COEFF. OF VARIATION (%)	=	2.97	=	5.86
Range	=	0.47	=	9.15
LOWEST READING	=	6.47	=	69.8
HIGHEST READING	=	6.94	=	79.0
NO. OF MEAS.	=	4	=	4
MEASURING TIME (s)	=		=	30